



ALFRED H. KNIGHT

CERTIFICATE NO.025459/7244/IST/IRST/TG
OF QUALITY TEST

Istanbul, 11.04.2000

<u>Hardness</u>	<u>depth (mm)</u>	<u>HV (300 gr. pyramid form diamond)</u>
	0.10	618
	0.20	550
	0.30	444
	0.40	429
	0.50	402
	0.70	402
	1.00	402
	1.50	402
	2.00	400

Testing time is 10 sec. for each case.

Remarks : Tensile Strength tests are made as per EN 10 002-1 : 1990 using "DARTEC RF -91146" and hardness tests are effected as per ASTM E 384 using " MATZUZAVA MHT-2"